

CLAIMS:

1. A multi-stack optical data storage medium for recording using a focused radiation beam having a wavelength λ and entering through an entrance face of the medium during recording, comprising at least:
 - a first substrate with present on a side thereof:
 - 5 - a first recording stack named L_0 , comprising a recordable type L_0 recording layer, and a first reflective layer present between the L_0 recording layer and the first substrate,
 - a second substrate with present on a side thereof:
 - a second recording stack named L_1 comprising a recordable type L_1 recording layer having a thickness t_{RL1} and a complex refractive index $n_\lambda - i*k_\lambda$ at the wavelength λ , a second reflective layer present adjacent the L_1 recording layer at a side most remote from the entrance face, and said second recording stack L_1 being present at a position closer to the entrance face than the L_0 recording stack,
 - a spacer layer, transparent for the radiation beam, sandwiched between the recording stacks, said transparent spacer layer having a thickness substantially larger than the depth of focus of the focused radiation beam,
 - 15 characterized in that the second reflective layer mainly comprises the metal Cu and has a thickness t_{MLn} selected from the range of 8 - 20 nm and the thickness t_{RL1} and k_λ of the recordable L_1 recording layer fulfils the formula $t_{RL1} * k_\lambda \leq 8$ nm.
- 20 2. A multi-stack optical data storage medium according to claim 1, wherein the recordable type L_1 recording layer comprises an organic dye.
3. A multi-stack optical data storage medium according to claim 2, wherein t_{RL1} is selected from the range of 70 – 125 nm.
- 25 4. A multi-stack optical data storage medium according to claim 2, wherein a first auxiliary layer, transparent for the radiation beam and with a thickness smaller than 15 nm, is present sandwiched between the second reflective layer and the spacer layer.

5. A multi-stack optical data storage medium according to claim 2 or 4, wherein a second auxiliary layer, transparent for the radiation beam and with a thickness smaller than 15 nm, is present sandwiched between the second reflective layer and the L₁ recording layer.
- 5
6. A multi-stack optical data storage medium according to claim 4 or 5, wherein the auxiliary layer comprises a material selected from the group of oxides and nitrides of silicon.
- 10 7. Use of an optical data storage medium as claimed in any one of the preceding claims for multi stack recording wherein the second recording stack L₁ has a reflectivity level of more than 18% and a transmission level of more than 50%.